



## Rigid PVC (Polyvinyl Chloride)

Rigid PVC (Polyvinyl Chloride) is a comparatively low cost plastic with an exceptionally good resistance to attack by a wide range of chemicals.

### Other properties are:

- Dimensional stability - almost no moisture absorption.
- Good electrical properties.
- Classified as self extinguishing.
- Easily fabricated.

### Chemical Resistance

At temperatures up to 60°C rigid PVC is resistant to most acids e.g. hydrochloric, phosphoric, sulphuric below 90% concentration and nitric below 50% concentration, alkalis, solutions of salts, gases and organic compounds such as fats, alcohols and aliphatic hydrocarbons. It is swollen and weakened by aromatic and chlorinated hydrocarbons, esters, ketones and aldehydes. It is not resistant to bromine, fluorine, chlorine gas in a hot damp environment and some concentrating oxidizing acids.

### AVAILABILITY - RIGID PVC

- Rod
- Sheet
- Section
- Machined Parts

MECHANICAL PROPERTIES	Test Method	UPVC	Units
Density	DIN 53479	1.38	g/cm <sup>3</sup>
Tensile Strength at Yield	DIN 53455	55	N/mm <sup>2</sup>
Elongation at Break	DIN 53455	20 - 40	%
Modulus of elasticity	DIN 53457	3000	N/mm <sup>2</sup>
Flexural Strength	DIN 53452	90	N/mm <sup>2</sup>
Impact Strength	DIN 53453	not broken	mJ/mm <sup>2</sup>
Notched Impact Strength	DIN 53453	3	mJ/mm <sup>2</sup>
Ball Indentation Hardness	DIN 53456	120	N/mm <sup>2</sup>
Rockwell Hardness	ASTM D785-51	R115	
Moisture Absorption	DIN 53495	0.2	%
Coefficient of Friction	DIN 53375	0.6	
THERMAL PROPERTIES			
Vicat Softening Point	DIN 53460	75	°C
Heat Deflection Temperature 1.8 N/mm <sup>2</sup>	DIN 53461	67	°C
Coefficient of Linear Thermal Expansion	DIN 53752	8.10 <sup>-5</sup>	°C <sup>-1</sup>
Thermal Conductivity	DIN 52612	0.15	W/mK
Inflammability	UL94	V - O	
Continuous Maximum Service Temperature		60	°C
Continuous Minimum Service Temperature		-15	°C
ELECTRICAL PROPERTIES			
Volume Resistivity	DIN 53482	10 <sup>15</sup>	ohm cm
Surface Resistivity	DIN 53482	10 <sup>13</sup>	ohm
Dielectric Strength	DIN 53481	40 - 50	kV/mm
Dielectric Constant	50 Hz	DIN 53483	4
	1 MHz		3
Dielectric Loss Factor	50 Hz	DIN 53483	0.015
	1 MHz		0.020
Tracking Resistance	KB Method	VDE 0303	>600
	KC Method		>600